US005149826A

United States Patent [19]

Delabouglise et al.

[11] Patent Number: 5,149,826

[45] Date of Patent: Sep. 22, 1992

[54] POLY[(3-PYRROLYL)ACETIC ACID]

[75] Inventors: **Didier Delabouglise; Francis Garnier,** both of Thiais, France

[73] Assignee: **Nippon Oil Co., Ltd.,** Tokyo, Japan

[21] Appl. No.: **637,631**

[22] Filed: **Jan. 4, 1991**

[30] **Foreign Application Priority Data**

Jan. 8, 1990 [JP] Japan 2-409

[51] **Int. Cl.**[5] **C07D 207/30;** C08F 26/06

[52] **U.S. Cl.** **548/518;** 526/258

[58] **Field of Search** 548/518; 526/258

[56] **References Cited**

U.S. PATENT DOCUMENTS

5,059,694 10/1991 Delabouglise et al. 548/518

Primary Examiner—Mary C. Lee
Assistant Examiner—Joseph K. McKane
Attorney, Agent, or Firm—Oblon, Spivak, McClelland, Maier & Neustadt

[57] **ABSTRACT**

A poly[(3-pyrrolyl)acetic acid] is here disclosed which is represented by the formula (I)



(I)

wherein n is an integer of 2 or more.

This polymer can be prepared by subjecting (3-pyrrolyl)acetic acid to electrolytic oxidation polymerization in the presence or absence of a salt. The polymer can be used as a pH sensor in which electrical properties change in accordance with a pH. Furthermore, it can also be used as electrodes for a secondary battery in which a cation transport electrolyte is used.

2 Claims, 1 Drawing Sheet